

NOVALK AC

We are now stocking the Novalk AC / PC clear topcoats and colours.

AC CLEAR TOP-COAT CLEAR TOPCOAT

AC CLEAR TOP-COAT	NAH15902
SHEEN	10% / 20% / 40% / 90%
MIX RATIO	10:1 with NCH999 catalyst
GRAVITY GUN	30% to 40% thinners ND4100
PUMP GUN	20% to 30% thinners ND4100
DRYING - SANDING	1st coat - 1 hour; 2nd coat - 2 hours
DRYING - FLIPPING	2 hours or 3 hours on bigger panels
RECOMMENDED	2/3 coat on coat at 100 microns
THINNERS	Recommended only to add thinners when using product. ONLY use Lacquerite ND4100 or ND4800, never recycled thinners or other thinners which have not been tested.
POT LIFE	Up to 72 hours with ND4100

NOVALK AC

We are now stocking the Novalk AC / PC clear topcoats and colours.

AC WHITE PRIMER PRIMER / PREP LAYER

AC WHITE PRIMER	NFH15920
PRODUCT	Includes white and tinted primers
MIX RATIO	10:1 NCH999 catalyst
GRAVITY GUN	20 to 25% thinners ND4100
PUMP GUN	10 to 15% thinners ND4100
DRYING - SANDING	2 hours
DRYING - FLIPPING	2 to 3 hours
RECOMMENDED	2 in one day at 140/150 microns
THINNERS	Recommended only to add thinners when using product. ONLY use Lacquerite ND4100 or ND4800, never recycled thinners or other thinners which have not been tested.

NOVALK AC

We are now stocking the Novalk AC / PC clear topcoats and colours.

AC COLOURS

FINISH COLOUR COATS

AC COLOURS	NAH15902 / NAH15921B
SHEEN	10% / 20% / 40% / 90%
GRAVITY GUN	40% thinners ND4100 — only add thinners when product is going to be used
PUMP GUN	30% thinners ND4100 — only add thinners when product is going to be used
MIX RATIO	10:1 mix with NCH999 catalyst
FLASH COAT	Can be flash coated
POT LIFE	48/72 hours with ND4100 thinners
DRYING - SANDING	2-3 hours
DRYING - FLIPPING	3 hours or 4 hours on bigger panels
THINNERS	For antiblooming - half thinners ND4100 and half thinners ND4800. Only add thinners when product is going to be used. ONLY use Lacquerite ND4100 or ND4800, never recycled thinners or other thinners which have not been tested.