

NOVALK PC

We are now stocking the Novalk PC clear topcoats and colours.

PC CLEAR TOP-COAT CLEAR TOPCOAT

PC CLEAR TOPCOAT	NAH15931
SHEEN	10% / 20% / 40% / 90%
GRAVITY GUN	20% to 30% thinners ND4100
PUMP GUN	10% to 20% thinners ND4100
DRYING TIME - SANDING	1st base coat - 1 hour
DRYING TIME – SANDING COAT ON COAT)	2nd coat - 2 hours
DRYING TIME - FLIPPING	1 hour on the first coat; 2 - 3 hours on bigger panels and second coat
RECOMMENDED	2 to 3 coats at 100 microns
THINNERS	For antiblooming - half thinners ND4100 and half thinners ND4800. Only add thinners when product is going to be used. ONLY use Lacquerite ND4100 or ND4800, never recycled thinners or other thinners which have not been tested.

NOVALK PC

We are now stocking the Novalk PC clear topcoats and colours.

PC PRIMERS PRIMER / PREP LAYER

PC WHITE PRIMER	NFH15910
GRAVITY GUN	30% thinners ND4100
PUMP GUN	20% thinners ND4100
DRYING TIME - SANDING	1 hour +
DRYING TIME - FLIPPING	1 hour or 2 hours on bigger panels
RECOMMENDED	2 coats in one day at 140/150 microns
THINNERS	Only add thinners to product when it's going to be used. ONLY use Lacquerite ND4100 or ND4800, never recycled thinners or other thinners which have not been tested.

PC CLEAR PRIMER (TINTED)	NFH15944
GRAVITY GUN	30% thinners ND4100
PUMP GUN	20% thinners ND4100
DRYING TIME - SANDING	1 hour +
DRYING TIME - FLIPPING	1 hour or 2 hours on bigger panels
RECOMMENDED	2 coats in one day at 140/150 microns
THINNERS	Only add thinners to product when it's going to be used. ONLY use Lacquerite ND4100 or ND4800, never recycled thinners or other thinners which have not been tested.

NOVALK PC

We are now stocking the Novalk PC clear topcoats and colours.

PC SANDING SEALER PREP LAYER

PC SANDING SEALER	NFH15900
GRAVITY GUN	20% thinners ND4100
PUMP GUN	10% thinners ND4100
DRYING TIME - SANDING	1 hour
DRYING TIME - FLIPPING	1 hour or 2 hours on bigger panels
RECOMMENDED	1 to 2 coats at 100 microns
THINNERS	ND4800 if needed for antiblooming. Only add thinners to product when it's going to be used. ONLY use Lacquerite ND4100 or ND4800, never recycled thinners or other thinners which have not been tested.

NOVALK PC

We are now stocking the Novalk PC clear topcoats and colours.

PC COLOURS FINISH COLOUR COATS

PC COLOURS	NAH15955 / NAH15911B
GRAVITY GUN	40% to 50% thinners ND4100
PUMP GUN	30% to 40% thinners ND4100
THINNERS	For antiblooming – half thinners ND4100 and half thinners ND4800. Only add thinners to product when it's going to be used. ONLY use Lacquerite ND4100 or ND4800, never recycled thinners or other thinners which have not been tested.